

TEST REPORT

Page 1 of 5

REPORT NUMBER : TURT240067031
APPLICANT NAME : Alpsan Alüminyum ve Plastik Profil San. Tic. A.Ş.
ADDRESS : Barış Mah. 1804 /4 Sk. No:3Gebze Kocaeli / TURKEY
TEL:0262 642 84 42FAX:0262 642 84 41
Attention : Mustafa Bekçi (mustafa.bekci@alpsan.com)
SAMPLE DESCRIPTION : One sample of Eloksal (Coated profile)
DATE IN : 30 May ,2024 (15:35:00)
DATE OUT : 11 June ,2024
MODEL/STYLE NO : 6063
REQUEST. Rohs Directive (EU) 2015/863 amending Annex II to Directive 2011/65/EU

		CONCLUSION
PART	DESCRIPTION	
Sample 1	Sample	Pass

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Unless otherwise is specified, all Pass or Fail results are given without uncertainty considered. The reported uncertainty is based on a standard uncertainty multiplied by a coverage factor k=2, providing a level of confidence of approximately 95%. The uncertainty evaluation has been carried out in accordance with ISO/IEC 17025 and TÜRKAK accreditation requirements. Tests marked (*) in this test report are not included in the TÜRKAK accreditation schedule for this laboratory. Intertek accredited by TÜRKAK under registration number [AB-0716-T] for [TS EN ISO IEC 17025] as test laboratory. Turkish Accreditation Agency (TURKAK) is a signatory to the European co-operation for Accreditation (EA) Multilateral Agreement (MLA) and to the International Laboratory Accreditation Cooperation (ILAC) Mutual Recognition Arrangement (MRA) for the recognition of test reports.



Melis Evci
Customer Care Executive



Kerem CAN
Consumer Products Operational Excellence Director

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna-34197 /ISTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertekcg.turkiye@intertek.com
<http://www.intertek-turkey.com>



TEST REPORT

11 June ,2024

REPORT : TURT240067031

Page 2 of 5

(A) TEST RESULT SUMMARY ACCORDING TO IEC 62321
Electrotechnical Products-Determination of Levels of Six Regulated Substances

TESTING ITEM	RESULT
	Sample 1
Cadmium (Cd) Content	ND
Chromium VI (Cr+6) Content (ppm) (for non- metal)	NA
Chromium VI (Cr+6) Content (µg/cm ²) (for metal)	ND
Lead (Pb) Content	27 ppm
Mercury (Hg) Content	ND
Flame Retardants	
Polybrominated Biphenyls (PBB)	NA
Monobromobiphenyl (MonoBB)	NA
Dibromobiphenyl (DiBB)	NA
Tribromobiphenyl (TriBB)	NA
Tetrabromobiphenyl (TetraBB)	NA
Pentabromobiphenyl (PentaBB)	NA
Hexabromobiphenyl (HexaBB)	NA
Heptabromobiphenyl (HeptaBB)	NA
Octabromobiphenyl (OctaBB)	NA
Nonabromobiphenyl (NonaBB)	NA
Decabromobiphenyl (DecaBB)	NA
Polybrominated Diphenyl Ethers (PBDE)	NA
Monobromodiphenyl Ether (MonoBDE)	NA
Dibromodiphenyl Ether (DiBDE)	NA
Tribromodiphenyl Ether (TriBDE)	NA
Tetrabromodiphenyl Ether (TetraBDE)	NA
Pentabromodiphenyl Ether (PentaBDE)	NA
Hexabromodiphenyl Ether (HexaBDE)	NA
Heptabromodiphenyl Ether (HeptaBDE)	NA
Octabromodiphenyl Ether (OctaBDE)	NA
Nonabromodiphenyl Ether (NonaBDE)	NA
Decabromodiphenyl Ether (DecaBDE)	NA
Phthalates	
Dibutyl phthalate (DBP) (84-74-2)	NA
Diethyl Hexyl Phthalate (DEHP) (117-81-7)	NA
Benzyl butyl phthalate (BBP) (85-68-7)	NA
Diisobutyl Phthalate (DIBP) (84-69-5)	NA

Remarks : ppm=Parts per million based on dry weight of sample
µg/cm²=Microgram per square centimetre
mg/kg with 50 cm²=Milligram per kilogram with 50 square centimetre
ND =Not detected NA =Not applicable NR =Not requested

TEST REPORT

11 June ,2024

REPORT : TURT240067031

Page 3 of 5

(B) REQUIREMENT :

SUBSTANCE	LIMITS	
Cadmium (Cd) Content	0.01 % (100 ppm)	
Chromium VI (Cr+6) Content (ppm) (for non metal)	0.1 % (1000 ppm)	
Chromium VI (Cr+6) Content (µg/cm ²) (for metal)	<u>Colorimetric result</u> < 0.10 µg/cm ² ≥ 0.10 µg/cm ² and ≤ 0.13 µg/cm ² > 0.13 µg/cm ²	<u>Qualitative Result</u> Negative Inconclusive Positive
Lead (Pb) Content	0.1 % (1000 ppm)	
Mercury (Hg) Content	0.1 % (1000 ppm)	
Flame Retardants	0.1 % (1000 ppm)	
Dibutyl Phthalate (DBP)	0.1 % (1000 ppm)	
Diethyl Hexyl Phthalate (DEHP)	0.1 % (1000 ppm)	
Benzyl Butyl Phthalate (BBP)	0.1 % (1000 ppm)	
Diisobutyl Phthalate (DIBP)	0.1 % (1000 ppm)	

TEST REPORT

11 June ,2024

REPORT : TURT240067031

Page 4 of 5

(C) TEST METHOD :

Testing Item	Testing Method	Reporting Limit	Uncertainty
Cadmium (Cd) Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic: 10 ppm / Metal: 4 ppm / Seramic: 5 ppm	Metal- Pb&Cd&Cr:±13% Metal-Hg:±12% Plastic:±9% Ceramic/Glass:±10% Carton:±7%
Lead (Pb) Content	With reference to IEC 62321-5:2013,by microwave or acid digestion and determined by ICP-OES	Plastic: 10 ppm / Metal: 4 ppm / Seramic: 5 ppm	
Mercury (Hg) Content	With reference to IEC 62321-4:2013/AMD1:2017,by microwave or acid digestion and determined by ICP-OES	Plastic: 10 ppm / Metal: 10 ppm / Seramic: 5 ppm	
Chromium VI (Cr6+) (For non-metal)	With reference to IEC 62321-7-2:2017,by alkaline digestion and determined by UV-VIS spectrophotometer	Plastic 25 ppm (PVC Based) / 8,33 ppm (Other)	Plastic-PVC ±12% Plastic-PP ±5% Ceramic/Glass ±5% Carton:±11%
Chromium VI (Cr6+) (For metal)	With reference to IEC 62321-7-1:2015 ,by boiling water extraction and determined by UV-VIS spectrophotometer	0,1 ppm with 50 cm2 (In testing solution)	±13%
PBBs/PBDEs	With reference to IEC 62321-6:2015,by solvent extraction and determined by GC/MS and HPLC	5 ppm	±15%
Phthalates	With reference to IEC 62321-8 (111/321/CD), by solvent extraction and determined by GC-MS.	50 ppm	±16%

TEST REPORT
REPORT : TURT240067031

11 June , 2024
Page 5 of 5

Sample 1



END OF TEST REPORT